



MULTI-PURPOSE PRIMER 067

Features

- Strong adhesion to interior and exterior substrates
- Quick drying – 1 hour recoat
- Low-VOC
- Provides a mildew resistant coating

Recommended For

Interior: Use on new or previously painted wood, plywood, drywall, ceiling tile, Formica®, Masonite®, ceramic tile, cured plaster, and wall coverings.

Exterior: Use on new or previously painted wood, aluminum, hardboard and vinyl siding, shingles, shakes, concrete, masonry, brick, and non-ferrous metal surfaces. On hard, non-porous surfaces, such as glazed ceramics and non-ferrous metal, **maximum adhesion and hardness** may take 3-4 days to develop.

General Description

A 100% acrylic, interior and exterior primer for all project needs. It combines all the qualities desired in a multi-purpose primer: strong adhesion for all surfaces, provides a mildew-resistant coating, quick drying, and low-VOC. Formulated to suppress most light stains.

Limitations

- Not recommended for sealing knots or over pine sap.
- Apply when surface and ambient temperature is above 40 °F.
- Not recommended for use on floor surfaces.

Product Information

Colors — Standard:

White (00)

Can add up to 2 fl. oz of Benjamin Moore® Gennex® colorant per gallon.

— Special Colors:

Contact your Benjamin Moore representative.

Certifications & Qualifications:

VOC compliant in all regulated areas

- Qualifies for LEED® v4 Credit
- Qualifies for CHPS low emitting credit (Collaborative for High Performance Schools)
- CDPH v1 Emission Certified
- Master Painters Institute MPI # 6, 39, 137, 137 X-Green™
- Class A (0-25) over non-combustible surfaces when tested in accordance with ASTM E-84
- Water Vapor Transmission: ASTM D1653 (method A): 7 perms

Technical Assistance

Available through your local authorized independent Benjamin Moore retailer. For the location of the retailer nearest you, call 1-866-708-9180 or visit www.benjaminmoore.com

Technical Data

White

Vehicle Type	100% Acrylic Latex	
Pigment Type	Titanium Dioxide	
Volume Solids	36 ± 1%	
Coverage per Gallon at Recommended Film Thickness	350 – 450 Sq. Ft.	
Recommended Film Thickness	– Wet	3.6 – 4.4 mils
	– Dry	1.3 – 1.6 mils
Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure color uniformity and minimize the disposal of excess paint.		
Dry Time @ 77 °F (25 °C) @ 50% RH	– To Touch	30 minutes
	– To Recoat	1 hour
High humidity and cool temperatures will result in longer dry, recoat and service times.		
Dries By	Evaporation, Coalescence	
Viscosity	98 ± 5 KU	
Flash Point	None	
Gloss / Sheen	Flat (< 10 @ 85°)	
Surface Temperature at Application	– Min.	40 °F
	– Max	90 °F
Thin With	Do Not Thin	
Clean Up Thinner	Clean Water	
Weight Per Gallon	10.3 lbs	
Storage Temperature	– Min.	40 °F
	– Max	90 °F

Volatile Organic Compounds (VOC)

29.5 Grams/Liter 0.24 Lbs./Gallon

Multi-Purpose Primer (067)

Surface Preparation

Surfaces to be painted must be clean, dry, and free of dirt, dust, grease, oil, soap, wax, scaling paint, water soluble materials, and mildew. Remove any peeling or scaling paint and sand these areas to feather edges smooth with adjacent surfaces. Glossy areas should be dulled. Drywall surfaces must be free of sanding dust.

New plaster or masonry surfaces must be allowed to cure before applying base coat. Cured plaster should be hard, have a slight sheen and maximum PH of 10; soft, porous or powdery plaster indicates improper cure. Never sand a plaster surface; knife off any protrusions and prime plaster before and after applying patching compound. Poured or pre-cast concrete with a very smooth surface should be etched or abraded to promote adhesion, after removing all form release agents and curing compounds. Remove any powder or loose particles before priming. Wood substrates must be thoroughly dry. Caution: Smooth planed clapboards or siding must be sanded thoroughly to break the "mill glaze" allowing proper penetration and adhesion.

Difficult Substrates: If the surfaces to be painted exhibit severe tannin or smoke staining, an alkyd based Benjamin Moore primer may be your best choice for conquering these severe conditions. Consult your Benjamin Moore retailer for further guidance.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Informational Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead

Primer/Finish Systems

New surfaces should be fully primed, and previously painted surfaces may be primed or spot primed as necessary. For best hiding results use Multi-Purpose Primer tinted to the approximate finish coat color. **Special Note:** Certain custom colors require a Deep Color Base Primer tinted to a special prescription formula to achieve the desired color. Consult your retailer.

Wood, and engineered wood products:

Primer: Multi-Purpose Primer (067)

Bleeding type woods, (cedar and redwood): Fresh Start® High-Hiding All Purpose Primer (046) or Fresh Start® Deck & Siding Primer (094)

Finish: 1 or 2 coats of the appropriate Benjamin Moore® finish coat

Drywall:

Primer: Multi-Purpose Primer (067)

Finish: 1 or 2 coats of the appropriate Benjamin Moore® finish coat

Plaster:

Primer: Multi-Purpose Primer (067)

Finish: 1 or 2 coats of the appropriate Benjamin Moore® finish coat

Masonry; Rough or Pitted:

Primer: Ultra Spec® Masonry Interior/Exterior Hi-Build Block Filler (571)

Finish: 1 or 2 coats of the appropriate Benjamin Moore® finish coat

Masonry; Smooth Poured or Pre-cast Concrete:

Primer: Multi-Purpose Primer (067) or Ultra Spec® Masonry Interior / Exterior 100% Acrylic Masonry Sealer (608)

Finish: 1 or 2 coats of the appropriate Benjamin Moore® finish coat

Ferrous Metal (Steel and Iron):

Primer: Ultra Spec® HP Acrylic Metal Primer (HP04) or Super Spec HP® Alkyd Metal Primer (P06)

Finish: 1 or 2 coats of the appropriate Benjamin Moore® finish coat.

Non-Ferrous Metal (Galvanized & Aluminum): All new metal surfaces must be thoroughly cleaned with Corotech® Oil & Grease Emulsifier (V600) to remove contaminants. New shiny non-ferrous metal surfaces that will be subject to abrasion should be dulled with very fine sandpaper or a synthetic steel wool pad to promote adhesion

Primer: Ultra Spec® HP Acrylic Metal Primer (HP04) or Multi-Purpose Primer (067)

Finish: 1 or 2 coats of the appropriate Benjamin Moore® finish coat.

Repaint, All Substrates: Prime bare areas with the primer recommended for the substrate above.

Application

Stir thoroughly before and during use. Apply one or two coats. **Paint Application:** For best results, use a premium Benjamin Moore® custom-blended nylon/polyester brush, premium Benjamin Moore® roller, or a similar product. Apply paint generously from unpainted area into wet area. This product can also be sprayed.

Spray, Airless: Fluid Pressure: 1500 – 2500

Tip: .013 - .017

Thinning/Clean Up

Thinning is unnecessary, but if required to obtain desired application properties, a small amount of clean water may be added. Never add other paints or solvents.

Clean Up: Use soap and water. Spray equipment should be given a final rinse with mineral spirits to prevent corrosion or follow state/local guidelines on solvent use.

USE COMPLETELY OR DISPOSE OF PROPERLY. Dry empty containers may be recycled in a can recycling program. Local disposal requirements vary; consult your sanitation department or state-designated environmental agency on disposal options.

We warrant satisfactory results if used according to label directions. If not satisfied return the unused portion to place of purchase with sales receipt. Material will be replaced or purchase price will be refunded. Since we have no control over surface preparation or application, THIS WARRANTY DOES NOT INCLUDE COST OF LABOR FOR APPLICATION OF PAINT. BENJAMIN MOORE SHALL IN NO EVENT BE LIABLE FOR INDIRECT, SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES. SOME STATES DO NOT ALLOW THE EXCLUSION OF INCIDENTAL OR CONSEQUENTIAL DAMAGES, SO THE LIMITATIONS OR EXCLUSIONS CONTAINED IN THE ABOVE WARRANTY MAY NOT APPLY TO YOU. This warranty gives you specific legal rights. You may also have other rights which vary from state to state.

Environmental Health & Safety Information

Use only with adequate ventilation. Do not breathe spray mist or sanding dust. Ensure fresh air entry during application and drying. Avoid contact with eyes and prolonged or repeated contact with skin. Avoid exposure to dust and spray mist by wearing a NIOSH approved respirator during application, sanding and clean up. Follow respirator manufacturer's directions for respirator use. Close container after each use. Wash thoroughly after handling.



WARNING Cancer and Reproductive Harm—
www.P65warnings.ca.gov

WARNING: This product contains isothiazolinone compounds at levels of <0.1%. These substances are biocides commonly found in most paints and a variety of personal care products as a preservative. Certain individuals may be sensitive or allergic to these substances, even at low levels.

FIRST AID: In case of eye contact, flush immediately with plenty of water for at least 15 minutes; for skin, wash thoroughly with soap and water. If symptoms persist, seek medical attention. If you experience difficulty breathing, leave the area to obtain fresh air. If continued difficulty is experienced, get medical attention immediately.

IN CASE OF SPILL – Absorb with inert material and dispose of as specified under "Clean Up".

**KEEP OUT OF REACH OF CHILDREN
PROTECT FROM FREEZING**

Refer to Safety Data Sheet for additional health and safety information.